

S1600 DATA SHEET

Typical Physical Properties

Colour:	White cross-linked polyethylene
Thickness:	1, 1.5 and 3mm
Density:	100 kg/m ³ (10 expansion)
Adhesion Strength:	1800 g/25mm (to stainless steel)
Shear Strength:	70 N/cm ² (aluminium to aluminium)
Tensile Adhesion:	28 N/cm ²
Roll Tack:	No:10
Temperature Range:	to 80°C

Parameter values are not guaranteed and will differ from lot to lot.

S1600
Is a cross-linked white polyethylene foam with acrylic adhesive on both sides.

- Excellent quick-stick properties.
- Dimensionally stable. Will not ooze, run or drip.
- Easily removable liner minimises stretching during installation.
- Good temperature resistance.
- Range of thicknesses available.

Application Guide

Surfaces should be clean before applying. Avoid touching adhesive surface before application.

Press firmly to ensure good adhesion.

Typical Application

Mirror mounting and interior mounting requiring good quick-stick properties.

Limited Warranty

For a period of six months from the date of first sale, warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our opinion, to refund the purchase price thereof.

The user assumes all other risks, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use this product. This warranty is in lieu of the warranties of merchantability, fitness for particular purpose, and all other warranties, expressed or implied. No deviation is authorised.

For more information, please contact: **3M Scotch-Bond** Ltd, 1000, The Parkway, Basingstoke, Hampshire, RG24 0BA, UK. Tel: 01256 332300. Fax: 01256 332301. Email: scotchbond@3m.co.uk

© 2000 3M Intellectual Property
3M, Scotch-Bond, and the Scotch-Bond logo are trademarks of 3M Company.
S1600-01